



## Deckshield ED HD

**CE** 13 PN-EN 1504-2 Te

RE B<sub>A</sub>-SL

Clo Wo

CR

Cla TE

fro

W

Ka

CH Res bar DC Me WI Tak

A flexible, solvent free, polyurethane car park deck coating system which provides waterproof wearing surface for exposed heavy wear areas.





#### Flexible

Resistant to cracking – flexible waterproof membrane

#### **UV Resistant**

100% UV stable formulation available to prevent the floor from yellowing



#### Slip Resistant:

Positively textured anti-slip surface minimizes slip and skid risks



#### **Chemical Resistant:**

Protects against diesel, fuel, antifreeze, hydraulic fluid, chlorides and battery acid

chnical Informati	chnical Information <sup>1</sup>				
EACTION TO FIRE					
-s1	EN 13501-1				
IP RESISTANCE <sup>2</sup>					
ass III et > 55	EN 1504 -2				
RACK BRIDGING ABILITY	BRIDGING ABILITY				
ass A3 (-20°C)	EN 1062-7				
MPERATURE RESISTANCE	PERATURE RESISTANCE				
om -35°C to +70°C (intermitter	35℃ to +70℃ (intermittent)				
ATER PERMEABILITY					
ursten test - Nil (Impermeable)	ten test - Nil (Impermeable)				
HEMICAL RESISTANCE					
sistant to petrol, diesel, antifre attery acids	o petrol, diesel, antifreeze, hydraulic fluids and ids				
ESISTANCE TO CHLORIDE IO	NS				
DT BD47/94: Appendix B, ethod B4,2(d)	No chloride ion penetration after 28 days				
EAR RESISTANCE					
ber Test: < 3000 mg wheel 22/1000 g /1000 cycles	EN ISO 5470-1				

# TENSILE STRENGTH/ RELATIVE ELONGATION (N/mm<sup>2</sup>/%)

1 day: 5.4 MPa/50.4% 7 days: 7.15 MPa/40.2% 28 days: 7.17 MPa/30.5%	BS 2782: Part 3 Method 320A Samples tested at 70°C		

FLEXIBILITY IN LOW TEMPERATURES

membrane at -20°C	MOAT 27: Memod 5.4.2	
TEAR STRENGTH		
Class III (≥20 Nm)	EN ISO 6272-1	
ADHESION BY PULL-OFF TEST	S	
Higher than concrete class C20/25 surface resistance (> 1.5 MPa)	EN 1542	





Mid Grey Traffic Blue

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local CPG Europe office.

#### **Model Specification**

System:	Deckshield ED HD	
Finish:	Gloss	
Thickness <sup>3</sup> :	Approx 3,0 mm	
Colour	According to the catalog	
Producer:	CPG Europe	
Supplier:	Tremco CPG Poland Sp. z o.o.	
Telephone	+48 22 879 89 07	

<sup>3</sup> In case of special usage requirements, the system can be applied in thickness up to 5.0 mm.

#### Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via website at www.flowcrete.com.pl.

#### Products Included in this System

Primer <sup>4</sup> :	Deckshield SF Natural quartz sand 0,1–0,3 mm Natural quartz sand 0,1–0,5 mm	
Elastic membrane:	Deckshield EM	
Main layer:	Deckshield SF Natural quartz sand 0,1–0,3 mm Natural quartz sand 1,4–2,0 mm	
Topcoat:	Deckshield Finish Deckshield Topcoat (UV resistant)	
<sup>4</sup> If other resins are used contact CPG Eastern Europe for further details. Detailed application instructions are available upon request.		

#### Speed of Cure

	+10°C	+20°C	+30°C
Light Traffic	30 hrs	16 hrs	10 hrs
Full traffic	36 hrs	24 hrs	16 hrs
Full chemical cure	12 days	7 days	5 days

#### Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pulloff test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements.* 


#### Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

#### **Crack Bridging Properties**

Using the flexible Deckshield Elastomeric Membrane enhances the crack bridging abilities of Deckshield flooring systems up to 2 mm wide cracks.

#### System Design



#### **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs, maintenance and cleaning. VOC content < 10 g/l.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as "CPG Polska") knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance. CPG Polska control take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.

[25/05/21]

CPG Eastern Europe ul. Marywilska 34, 03-228 Warsaw, Poland tel.: +48 22 879 8907 email: poland@cpg-europe.com



### www.flowcrete.com.pl