

# **Deckshield ED**

13 PN-EN 1504-:

A flexible polyurethane flexible car park deck coating system providing a colourful crack bridging, waterproof surface for exposed decks of car parks.





## **Flexible**

Resistant to cracking – flexible waterproof membrane



#### **UV** Resistant

100% UV stable formulation available to prevent the floor from yellowing



# Slip Resistant:

Positively textured anti-slip surface minimizes slip and skid risks



### **Chemical Resistant:**

Protects against diesel, fuel, antifreeze, hydraulic fluid, chlorides and battery acid

## Technical Information<sup>1</sup>

lechnical Information'				
REACTION TO FIRE				
B <sub>f</sub> -s1	EN 13501-1			
SLIP RESISTANCE <sup>2</sup>				
Class III Wet > 55	EN 1504 -2			
CRACK BRIDGING ABILITY				
Class A3(-20°C)	EN 1062-7			
TEMPERATURE RESISTANCE				
from -35°C to +70°C (intermittent)				
WATER PERMEABILITY				
Karsten test - Nil (Impermeable)				
CHEMICAL RESISTANCE				
Resistant to petrol, diesel, antifreeze, hydraulic fluids and battery acids				
RESISTANCE TO CHLORIDE IONS				
DOT BD47/94: Appendix B, Method B4,2(d)	No chloride ion penetration after 28 days			
WEAR RESISTANCE				

# 1 day: 5.4 MPa/50.4% BS 2782: Part 3 Method 320A

7 days: 7.13 MPa/40.2% 32UA 28 days: 7.17 MPa/30.5% Samples tested at 70°C

TENSILE STRENGTH/ RELATIVE ELONGATION

## FLEXIBILITY IN LOW TEMPERATURES

No damage of the membrane at -20°C

Taber Test: < 3000 mg wheel H22/1000 g /1000 cycles

MOAT 27: Method 5.4.2

#### TEAR STRENGTH

 $(N/mm^2/\%)$ 

Class III (≥20 Nm)

EN ISO 6272-1

EN ISO 5470-1

#### ADHESION BY PULL-OFF TESTS

Higher than concrete class C20/25 surface resistance (> 1,5 MPa) EN 1542









Arabian Yellow

Forest Green

Dark Grey

Tile Red





Mid Grey

Traffic Blue

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local CPG Europe office.

# **Model Specification**

System:	Deckshield ED
Finish:	Gloss
Thickness <sup>3</sup> :	Approx. 2,0 mm
Colour	According to the catalog
Producer:	CPG Europe
Supplier:	Tremco CPG Poland Sp. z o.o.
Telephone	+48 22 879 89 07

<sup>&</sup>lt;sup>3</sup> In case of special usage requirements, the system can be applied in thickness up to 5.0 mm.

#### **Installation Service**

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via website at www.flowcrete.com.pl.

## Products Included in this System

Elastic membrane: Deckshield EM  Main layer: Deckshield SF		Natural quartz sand 0,1 – 0,3 mm Natural quartz sand 0,1 – 0,5 mm $$
Main layer: Deckshield SF	astic membrane:	Deckshield EM
	ain layer:	Deckshield SF Natural quartz sand 0,1–0,3 mm Natural quartz sand 0,8–1,2 mm
Topcoat:  Deckshield Finish Deckshield Topcoat (UV resistant)	pcoat:	Deckshield Topcoat

<sup>&</sup>lt;sup>4</sup> If other resins are used contact CPG Eastern Europe for further details.

# Speed of Cure

	+10°C	+20°C	+30°C
Light Traffic	30 hrs	16 hrs	10 hrs
Full traffic	36 hrs	24 hrs	16 hrs
Full chemical cure	12 days	7 days	5 days

## **Substrate Requirements**

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the Flowcrete Resin Flooring Substrate Requirements.


# Aftercare - Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

# **Crack Bridging Properties**

Using the flexible Deckshield Elastomeric Membrane enhances the crack bridging abilities of Deckshield flooring systems up to 2 mm wide cracks.

## System Design



#### **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs, maintenance and cleaning.

VOC content < 10 g/l.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as "CPG Polska") knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, CPG Polska cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date names and building principles, and also safely, typigene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.

[25/05/21]



Detailed application instructions are available upon request.