

# Flowshield LXP HD (2-3 mm)

A heavy duty, self-smoothing, solvent free, flexible, coloured, polyurethane based floor coating.



#### Seamless:

Delivers a seamless finish, except for underlying slab joints.



#### Chemical Resistant:

Excellent resistance to cleaning agents, sugars and acids.



#### Easy to Clean:

Seamless installation ensures dirt and dust are easily cleaned away.




#### Low Odour:

Solvent free and exhibits low odour during application.




Mid Grey 280 Tile Red 637

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.



## Technical Profile\*

EN 13501-1	B <sub>∉</sub> -s	B <sub>ff</sub> -s1		
IMPACT RESISTANCE				
EN ISO 6272	111	 Nm		
TEMPERATURE RESIS	STANCE			
Tolerant of sustained te		ures up <u>to 60°</u>	2	
WEAR RESISTANCE				
EN 13892-5	Abr	Abrasion quantity 2.25 cm <sup>3</sup>		
BOND STRENGTH		<u> </u>		
EN 1542	2.0	N/mm <sup>2</sup>		
ELONGATION AT BRE				
BS 6319		30%		
WATER PERMEABILIT				
Karsten Test		Nil (impermeable)		
TEAR STRENGTH	انتقال کے			
BS 6319	11	11 MPa		
SLIP RESISTANCE** (				
EN 13036-4 / BS 7976 (typical values for 4-S rubber slider)		Dry >40 low slip potential		
FLEXURAL STRENGTI	 H			
EN 13892-2		>20 N/mm <sup>2</sup>		
TENSILE STRENGTH				
BS 6319-7	>1:	>15 N/mm <sup>2</sup>		
ΤΟΧΙCITY				
Taint free to sensitive fo	odstuffs	(when <u>cured</u> )		
BS 8204-6 / FeRFA				
Туре 5				
SPEED OF CURE	10°C	20°C	30°C	
Light traffic	36 hrs	24 hrs	12 hrs	
Full traffic	72 hrs	48 hrs	24 hrs	
Full chemical cure	12 day	s 7 days	7 days	
These figures are trained	rties achieve	ed in laboratory tes	its at 20°C ai	



# www.flowcrete.co.uk

#### **Model Specification**

Product Flo

Flowshield LXP HD

Preparatory work and application in accordance with manufacturer's instructions.

#### Products Included In This System

Primer	Concrete: Deckshield SF Primer @ 0.3 kg/m <sup>2</sup> (Porous substrate may require 2 coat Steel: Peran Primer W @ 0.25 kg/m <sup>2</sup> Wood: Deckshield SF Primer @ 0.3 kg/m <sup>2</sup> Asphalt: Deckshield SF Primer	
	$@ 0.3 \text{ kg/m}^2$ (Porous substrate may require 2 coats)	
Coating	Flowshield LXP HD (density 1.8 kg/l) @ 3.6 kg/m² for 2 mm	

For slip resistant dressings, please consult our Technical Advisors.

Detailed application instructions are available upon request.

#### Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Flowshield system.

#### **Installation Service**

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

#### Aftercare

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Terms and Conditions of Sale', copies of which can be obtained on request.

#### **Environmental Considerations**

The finished system is assessed as nonhazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

#### Note

Flowshield LXP HD is not colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in light colours and blues but does not compromise the product's flexibility or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [27/02/19, 01 UK]

## www.flowcrete.co.uk

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.