

# Flowshield SK (2 mm)

A hygienic self-smoothing resin floor finish with excellent resistance to chemicals and SKYDROL hydraulic fluids.



## Attractive:

Enhances the appearance of working environment.



## **Chemical Resistant:**

Resistant to SKYDROL, hydraulic fluids and other chemicals.



## Easy to Clean:

Easy to clean and sterilise, low maintenance requirement.



# Hard Wearing:

Ideal for areas with sustained heavy foot traffic.









Beige 326

Dark Grey 281 Forest Green

Goosewing Grey 222









Light Grey 232 Mid Grey 280 Tile Red 637

Traffic Blue 446

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

# Technical Profile\*

	-	-	_	-0	-		
ы	υ	ы	υ	LU	C.	A 1	11 L
ш	IN	ш	N	I BOI	DТ	<b>7</b> 411	<b>ICE</b>

EN 13501-1

B<sub>0</sub>-s1

#### **IMPACT RESISTANCE**

EN ISO 6272

15 Nm

#### TEMPERATURE RESISTANCE

Tolerant up to 70°C (intermittent) or 50°C (sustained)

#### **WEAR RESISTANCE**

EN 13892-5

Abrasion quantity < 0.5 cm<sup>3</sup>

#### **BOND STRENGTH**

EN 13892-8

>2.5 N/mm<sup>2</sup>

#### WATER PERMEABILITY

Karsten test

Nil (impermeable)

# SLIP RESISTANCE\*\* (in accordance with HSE and UKSRG guidelines)

(typical values for 4-S rubber slider)

EN 13036-4 / BS 7976-2 Dry >40 low slip potential

# **COMPRESSIVE STRENGTH**

EN 13892-2

55 N/mm<sup>2</sup>

#### **FLEXURAL STRENGTH**

EN 13892-2

35 N/mm<sup>2</sup>

## TENSILE STRENGTH

BS 6319-7

25 N/mm<sup>2</sup>


## BS 8204-6 / FeRFA

Type 5

SPEED OF CURE	10°C	20°C	30°C
Light Traffic	24 hrs	12 hrs	6 hrs
Full Traffic	72 hrs	48 hrs	24 hrs
Full Chemical Cure	12 days	7 days	7 days

<sup>\*</sup>These figures are typical properties achieved in laboratory tests at  $20^{\circ}\text{C}$  and at 50% Relative Humidity.

<sup>\*\*</sup>The slipperiness of flooring materials can change significantly due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.



or any other information please contact your local Flowcrete Technical Department

# **Model Specification**

Product	Flowshield SK
---------	---------------

Preparatory work and application in accordance with manufacturer's instructions.

# **Products Included In This System**

Primer	Flowprime @ 0.25 kg/m² (Porous substrates may require 2 coats)
Topping	Flowshield SK @ 3.6 kg/m <sup>2</sup>

Detailed application instructions are available upon request.

## **Substrate Requirements**

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Flowshield SK system.

## Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme.

Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

#### **Aftercare**

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Terms and Conditions of Sale', copies of which can be obtained on request.

#### **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

#### Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [11/12/18, 01 UK]