

# Peran Comfort (2-3 mm)

A matte, self-smoothing, flexible polyurethane coating ideal for a minimalist, modern and contemporary environment.



## **Acoustic Resistance:**

Resilient acoustic, noise reduction and sound dampening.



## **Soft & Comfortable:**

Very soft feel underfoot, hard wearing and comfortable floor to walk on.



## **UV** Resistance:

Offers superior UV stability in the aliphatic coating and topcoat.



# Eco-Friendly & M1 Certified:

Low VOC, emissions and M1 Certified system.



## Temperature Resistant:

Tolerant of sustained temperatures up to 40°C.



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

# Technical Profile\*


REACTION TO FIRE		
EN 13501-1	B <sub>ff</sub> -s1	
IMPACT RESISTANCE		
EN ISO 6272	IR20	
WEAR RESISTANCE		
EN 13892-5	RWA300	
ELONGATION AT BREAK		
DIN 53504	50–100%	
SHORE A & D HARDNESS		
DIN 53505	D ≈ 40, A ≈ 80	
RELEASE OF CORROSIVE SUBSTANCES		
SR (Synthetic resin screed)		
WATER PERMEABILITY		
Karsten Test	Nil (Impermeable)	
<b>VOC</b> - ISO 16000-9 & CEN/TS 16516 (EN 16402)		
Emission speed TVOC: <0.100 mg/m²h after 28 days		
SLIP RESISTANCE*** (in accordance with HSE and UKSRG guidelines)		
EN 13036-4 / BS 7976-2 (typical values for 4-S rubber slider)	Dry 56 low slip potential Wet 26 moderate slip potential	
BS 8204-6 / FeRFA		

SPEED OF CURE***	10°C	20°C	30°C
Light traffic	48 hrs	24 hrs	16 hrs
Full traffic	4 days	2 days	2 days
Full chemical cure	14 days	7 days	4 days

Type 5

\*These figures are typical properties achieved in laboratory tests at  $20^\circ\text{C}$  and at 50% Relative Humidity.

\*\*\*The slipperiness of flooring materials can change significantly due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.



\*\*Cure times at temperatures between 0–30°C can be achieved by altering the quantity of catalyst used. For applications falling outside of this temperature range, please contact your local Flowcrete Technical Department.





# **Model Specification**

Product	Peran Comfort
Finish	Matte

Preparatory work and application in accordance with manufacturer's instructions.

## Products Included in This System

Standard system:		
Primer	Hydraseal DPM Natural @ 0.3 kg/m² (2 coats for porous substrates)	
Topping	Peran Comfort @ 2.6 kg/m² for 2mm or @ 3.9 kg/m² for 3mm	
Sealer	Flowseal PU Matte (Ultra) @ 0.1 kg/m² total for 2 coats	

Medium Flexibility system:		
Primer	Hydraseal DPM Natural @ 0.3 kg/m² (2 coats for porous substrates) Deckshield SF @ 1.0 kg/m²	
Topping	Peran Comfort @ 2.0 kg/m² for 1.5mm	
Sealer	Flowseal PU Matte (Ultra) @ 0.12 kg/m² total for 2 coats	

Detailed application instructions are available upon request.

## **Substrate Requirements**

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH in accordance with BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran Comfort system.

## Installation Service

The installation should be carried out by

a Flowcrete approved contractor with a documented quality assurance scheme.

Obtain details of our approved contractors by contacting our customer service team or enquiring via www.flowcrete.co.uk.

#### **Notes**

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change. Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface.

## **Aftercare**

Clean regularly in conjunction with a neutral detergent (or mild alkaline detergent for stubborn stains). A satin/ matte protective emulsion (e.g. TASKI Jontec Matte) may be applied to the surface of the Peran Comfort system if required, as part of the ongoing maintenance programme. In cases where cleaning companies carry out maintenance they should to be instructed to use a floor polish with the same gloss factor as Flowseal PU Matte (Ultra).

## Important Notes

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Terms and Conditions of Sale', copies of which can be obtained on request.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [04/12/18, 01 UK]