

Peran ESD STB Compact

(3 mm)

An epoxy-based, slip-resistant floor system that disperses static electricity.

Method 1: Semi-conductive coating, 106–109 Ω Method 2: Conductive coating, 103–106 Ω



Attractive:

Enhances the appearance of working environment.



Anti-Static:

Meets EN IEC 61340-5-1 anti-static requirements.



Hygienic:

Provides a seamless finish that is easy to clean and maintain.



Hard Wearing:

Ideal for areas with sustained medium to heavy foot traffic.









Grey 7710 Red 7720

Blue 7730

. .

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

Technical Profile*

ELECTRICAL RESISTANCE

| ELECTRICAL RESISTA | NCE | | | |
|---|---------------------|--------------------------------------|-----------------|--|
| EN IEC 61340-5-1 | 5×104 | – 1×10º Ω | | |
| REACTION TO FIRE | | | | |
| EN 13501-1 | B _{fl} -s1 | | | |
| IMPACT RESISTANCE | | | | |
| EN ISO 6272 | 15 Nm | | | |
| TEMPERATURE RESIS | TANCE | | | |
| Tolerant up to 70°C (in | termittent) c | r 50°C (sus | stained) | |
| WEAR RESISTANCE | | | | |
| EN 13892-5 | Abrasic | Abrasion quantity <1 cm ³ | | |
| BOND STRENGTH | | | | |
| EN 13892-8 | >2.5 N | √/mm² | | |
| SLIP RESISTANCE*** | (in accordance | with HSE & UKS | GRG guidelines) | |
| EN 13036-4 / BS 7976 (typical values for 4-S rubber slider) | -2 Dry > - | Dry > 40 low slip potential | | |
| COMPRESSIVE STREN | IGTH | | | |
| EN 13892-2 | >40 N | >40 N/mm ² | | |
| FLEXURAL STRENGTH | 1 | | | |
| EN 13892-2 | 15 N/r | 15 N/mm ² | | |
| TENSILE STRENGTH | | | | |
| BS 6319-7 10 | | 10 N/mm ² | | |
| BS 8204-6 / FeRFA | | | | |
| Туре б | | | | |
| SPEED OF CURE | 10°C | 20°C | 30°C | |
| Light traffic | 36 hrs | 24 hrs | 16 hrs | |
| Full traffic | 72 hrs | 48 hrs | 48 hrs | |

*These figures are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.


12 days

7 days

7 days

Full chemical cure

**The slipperiness of flooring materials can change significantly due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.





www.flowcrete.co.uk

Model Specification

| System | Peran ESD STB Compact |
|--------|-----------------------|
| Finish | Gloss |

Preparatory work and application in accordance with manufacturer's instructions.

Products Included In This System

| Primer | Peran STC @ 0.3 kg/m ² Conductive Grid required for Method 2 |
|---------|---|
| Primer | Peran ESD Primer @ 0.4 kg/m² |
| Scatter | Peran ESD Compact Primer sand @ 0.5 kg/m ² |
| Coating | Peran STC + Compact White (STC Filler) @ 2.0 kg/m ² |
| Scatter | Peran ESD STB Filler C @ 3.5 kg/m ² |
| Topcoat | Peran STC @ 0.15 kg/m ² |

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran ESD STB system.

Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

Aftercare

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent. Strong solvents such as acetone and thinners etc. should not be used. Damaged or worn coatings are best rectified by an authorised Flowcrete contractor.

Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change. Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Environmental Considerations

The finished system is assessed as nonhazardous to health and the environment. The long service life and seamless surface reduce the need for repairs and maintenance. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained application teams.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [11/12/18, 01 UK]

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.