

# Peran STB Compact (3 mm)

A hard wearing, decorative resin floor with natural quartz granules in a clear resin binder.



#### Attractive:

Decorative floor finish that delivers the wow-factor underfoot.



#### Wear Resistant:

Excellent general wear, tear, impact and chemical resistance underfoot.



#### Easy-to-Clean:

Seamless, hygienic finish that is easy to clean and maintain.

## Commercial







Dark Grey 703

Beige 101

Biscuit 102



601

Grass Green Light Grey 701 Mid Blue 501 Mid Grey 702

Black 901

## Industrial









Grey 704



Green 602

Red 301



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.



Low emission systems with M1 Certification are available. For more information, contact your local Flowcrete office.


## **Technical Profile\***

FIRE RESISTANCE		
EN 13501-1	B <sub>fl</sub> -s1	
WEAR RESISTANCE		
EN 13892-5	Abrasion quantity 1 cm <sup>3</sup>	
TEMPERATURE RESISTANCE		
Tolerant up to 70°C (intermittent) or 50°C (sustained)		
IMPACT RESISTANCE		
EN ISO 6272	15 Nm	
BOND STRENGTH		
EN 13892-8	>2.5 N/mm <sup>2</sup>	
WATER PERMEABILITY		
Karsten Test	Nil (Impermeable)	
VAPOUR PERMEABILITY		
ASTM E96:90	1.36 g / m² / mm / 24 hrs	
SLIP RESISTANCE**		
BS 7976-2 (typical values for 4-S rubber slider)	Dry >40 low slip potential	
COMPRESSIVE STRENGTH		
EN 13892-2	>40 N/mm <sup>2</sup>	
FLEXURAL STRENGTH		
EN 13892-2	15 N/mm <sup>2</sup>	
TENSILE STRENGTH		
BS 6319-7	10 N/mm <sup>2</sup>	
BS 8204-6 / FeRFA		
Туре 4		

SPEED OF CURE	10°C	20°C	30°C
Light Traffic	36 hrs	24 hrs	16 hrs
Full Traffic	72 hrs	48 hrs	48 hrs
Full Chemical Cure	12 days	7 days	7 days

\*These figures are typical properties achieved in laboratory tests at  $20\,^\circ\text{C}$  and at 50% Relative Humidity.

\*\*The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/ or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requiremen for wet conditions and/ or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.



# www.flowcrete.co.uk

## **Model Specification**

System	Peran STB Compact
Finish	Matte

Preparatory work and application in accordance with manufacturer's instructions.

### Products Included In This System

Primer	Peran STC @ 0.25 kg/m <sup>2</sup>
Scatter	Natural Quartz size 5F (1.0–1.8 mm) @ 0.5 kg/m <sup>2</sup>
Bodycoat	Peran STC @ 1.0 kg/m <sup>2</sup> mixed with: Compact White (STC Filler) @ 1.0 kg/m <sup>2</sup>
Scatter	Coloured Quartz Size 7/8 @ 3.5 kg/m² (full blind)
Sealer	Peran STC @ 0.2 kg/m² and Flowseal PU Matte @ 0.08 kg/m²

Detailed application instructions are available upon request.

### Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran STB system.

### Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

#### Aftercare

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

### **Environmental Considerations**

The finished system is assessed as nonhazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

#### Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [11/12/18, 01 UK]

# www.flowcrete.co.uk