

# Deckshield ID (2-3 mm)

A flexible and durable polyurethane for use on intermediate car park decks. Ensuring safety underfoot with enhanced traction.



# **Independently Certified:**

Tested & certified to OS8 and EN 1504-2.



# Slip Resistant:

Positively textured anti-slip surface minimises slip and skid risks.



### **Chemical Resistant:**

Protects against diesel, fuel, antifreeze, hydraulic fluid, chlorides & battery acid.



### Noise Reducing:

Enhanced traction underfoot minimises unpleasant noise from tyre squeal.



## Temperature Resistant:

Softens over 70°C and hardens on cooling.







Mid Grey

Dark Grey

Forest Green Traffic Purple





Traffic Blue

Tile Red

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

### **Technical Profile**

EN 1504-2:2005 Part 2: Surface **Protection Systems for Concrete** 

CLU	חח	FCI		-	CE
SLI	אט	EVI		ЛΝ	
JLII	I 1\	LUI	וט	VATE	UL.

UNE-EN 13036-4:2003 Class I: >40 Wet Test

#### **REACTION TO FIRE**

EN 13501-1  $B_{H}$ -s1

#### **BOND STRENGTH**

Measurement of Bond Strength by Pull-off

UNE-EN 1542:1999

#### WATER VAPOUR TRANSMISSION

Diffusion-equivalent Air Layer Thickness (Sd)

UNE-EN ISO 7783:2012

Class II:  $5 \le Sd \le 50 \text{ m}$ 

#### LIQUID WATER PERMEABILITY

UNE-EN 1062-3:2008

 $< 0.1 \text{ Kg/m}^2 \times h^{0.5}$ 

#### CARBON DIOXIDE PERMEABILITY

Diffusion-equivalent Air Layer Thickness (Sd)

UNE-EN ISO 7783:2012 >50 m

#### ADHESION AFTER THERMAL COMPATIBILITY

With De-icing Salt Immersion & Thunder Shower Cycling

UNE-EN 13687-1&2:2002 > 1.5 MPa

#### ABRASION RESISTANCE

Taber

UNE-EN ISO 5470-1:1999

Weight loss <3000 mg

#### IMPACT RESISTANCE

UNE-EN ISO 6272-1:2012 | Class III: >20 Nm

#### RESISTANCE TO SEVERE CHEMICAL ATTACK

UNE-EN 13529:2005 Group 1, 3 & 10

No defects & reduction in Shore Hardness < 50%

30°C

#### **DETERMINATION OF LINEAR SHRINKAGE**

UNE-EN 12617-1:2004

< 0.3%

SPEED OF CURE	10°C	20°C
Light Traffic	30 hrs	16 hrs

Light Traffic	30 hrs	16 hrs	10 hrs
Full Traffic	36 hrs	24 hrs	16 hrs
Full Chemical Cure	12 days	7 days	5 days

Typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity for a model specification.

# **Model Specification**

System	Deckshield ID
Finish	Gloss


Preparatory work and application in accordance with manufacturer's instructions.

# **Products Included In This System**

Deckshield ID for normal wear areas (e.g. parking bays and lighter traffic).

Deckshield ID-HD for heavier wear areas (e.g. drive aisles, turning points and ramps).

Deckshield ID-Ramp for very heavier wear areas (e.g. sole entry/exit ramps and turning points).



# **Substrate Requirements**

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. Substrate should be dry to 75% RH as per BS8203.

NB: Technical proposals are written for each installation to meet the client's particular requirements, the final thickness will be dependent upon the specification.

#### Installation Service

The installation should be carried out by a Deckshield approved contractor with a documented quality assurance scheme.

Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk

## Important Notes

Please contact our Technical Advisors for details of specialist companies to supply line-marking, which can be re-coated throughout the life of the Deckshield system.

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

# Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

#### **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained application teams.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [03/12/19, 01 UK]