




# Flowchem VE SL

Self smoothing shrinkage compensated vinyl ester resin based floor screed system with excellent chemical and mechanical resistance.





# Temperature Resistant:

Resistant to intermittent temperatures of up to  $145^{\circ}C$ 



#### **Chemical Resistant:**

Protects against a variety of aggressive acids, solvents caustics and chemicals



# Fast Cure:

Accelerated cure time, providing an operational surface in just 12 hours

Wear resistancee Excellent abrasion and good impact resistance

Tec	hnic	al P	rofi	e <sup>1</sup>

SLIP RESISTANCE				
Dry > 40	BS7976:PART 2			
TEMPERATURE RESISTANCE				
To 145°C				
VOLUME SHRINKAGE				
< 0,004 % RILL 4 2.5.3.2.1				
BARCOL HARDNESS				
> 40	ASTM 2583			
E-MODULUS				
3,1 GPa	ASTM D-695			
COMPRESSIVE STRENGTH				
120 MPa	ASTM D-695			
FLEXURAL STRENGTH				
100 MPa	ASTM D-790			
TENSILE STRENGTH				
50 MPa	ASTM D-638			
ADHESION				
> 4 MPa (Substrate failure)				
SPEED OF CURE <sup>2</sup>	20°C			
Light Traffic	12 h			
Full Traffic	24 h			
Full Chemical Cure	72 h			

# Standard colour chart



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

# **Model Specification**

Model Specification	Flowchem VE SL
	N
Finish	Matt
Thickness	approx. 3 mm
Colour	See standard colour chart
Producer:	Flowcrete Group Ltd
Supplier:	Flowcrete Polska Sp. z o.o.
Telephone:	+48 22 879 89 07

#### Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting Flowcrete Polska or enquiring via our website at www.flowcrete.com.pl.

#### Products Included in this System

Primer:	Flowchem VE Primer	
Main layer:	Flowchem VE SL	


#### Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

#### Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pulloff test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% moisture content per weight) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements.* 

### System Design



# **Environmental Considerations**

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Flowcrete Polska Sp. z o.o. (further related as "Flowcrete") knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quilty of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, Flowcrete cannot take responsibility in case of failure to conform with information in distructions included in this System Data Sheet or, respectively, written recommendations from authorized Flowcrete representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact. Flowcrete Folska

[25/01/18]

Flowcrete Central & Eastern Europe ul. Marywilska 34 03-228 Warsaw Poland Tel: +48 22 879 8907 Fax: +48 22 879 8918 Email: poland@flowcrete.com