

Peran ESD SL



A solvent free resin based floor topping formulated as part of an electrostatic dissipative flooring system.



Electrostatic Dissipative:

Used in areas where it is necessary to disperse static electricity



Meets requirements:

Meets anti-static requirements of EN 61340-5-1 and EN 61340-4-5



Smooth surface:

Waterproof, non-porous surface, easy to clean



Abrasion resistant:

Used in dry process areas where the floor is subjected to medium to heavy duty foot traffic and medium intensity trolley, pallet truck and rubber wheeled forklift traffic

Technical Information¹

ELECTRICAL RESISTANCE			
$5 \times 10^4 \Omega \leq R_u \leq 1 \times 10^6 \Omega$	EN 61340-5-1		
REACTION TO FIRE			
C _{fi} -s1	EN 13501-1		
SLIP RESISTANCE ²			
Dry > 40	EN 13036-4		
VAPOUR PERMEABILITY			
0,4 g/m ² /mm/24 h	ASTM E96:90		
TEMPERATURE RESISTANCE			
Up to +60°C			
WATER PERMEABILITY			
Karsten test - Nil (Impermeable)			
WEAR RESISTANCE			
RWA1	EN 13892-5		
FLEXURAL STRENGTH			
> 40 N/mm ²	EN 13892-2		
TENSILE STRENGTH			
> 25 N/mm ²	BS 6319-7		
IMPACT RESISTANCE			
IR17	EN ISO 6272-1		
BOND STRENGTH			
B2,7	EN 13813		
SPEED OF CURE			
	+10°C	+20°C	+30°C
Light Traffic	36 hrs	16 hrs	12 hrs
Full traffic	72 hrs	48 hrs	36 hrs
Full chemical cure	12 days	7 days	5 days

Standard colour chart



The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local CPG Europe office.

¹The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site. ²The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from CPG Eastern Europe), the degree of abrasion, maintenance and the nature of the dirt.

Model Specification

System:	Peran ESD SL
Finish:	Gloss
Thickness:	min. 1,5 mm
Colour	According to the catalog
Producer:	CPG Europe
Supplier:	Tremco CPG Poland Sp. z o.o.
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System³

Primer:	Peran STC (Protop 1000)
Antistatic Primer	Copper tape; Peran ESD Primer/ Peran ESD Primer WB;
Topping:	Peran ESD SL

³ If other resins are used contact CPG Eastern Europe for further details.

Detailed application instructions are available upon request.


Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

System Design



Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as „CPG Polska”) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer’s control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, CPG Polska cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.

25/05/21

CPG Eastern Europe
ul. Marywilska 34, 03-228 Warsaw, Poland
tel.: +48 22 879 8907
email: poland@cpg-europe.com

 **Construction
Products Group**
Europe

www.flowcrete.com.pl