

## Peran ESD STB Compact

Epoxy-based floor system that disperses static electricity. It gives a slip-resistant surface.



### Electrostatic discharge properties:

Used in areas where it is necessary to disperse static electricity



### Compliance with standards:

Meets EN 61340-5-1 and EN 61340-4-5 requirements



### Slip-resistance:

Can be applied in wet and dry processing areas delivering safe finish



### Hard wearing:

High scratch, impact and chemical resistance

## Technical Information<sup>1</sup>

### ANTISTATIC PROPERTIES:

$5 \times 10^4 \Omega \leq R_u \leq 1 \times 10^6 \Omega$  EN 61340-4-1

### REACTION TO FIRE

B<sub>fl</sub>-s1 EN 13501-1

### SLIP RESISTANCE<sup>2</sup>

Dry > 40 EN 13036-4

### TEMPERATURE RESISTANCE

Tolerant up to +50°C

### WATER PERMEABILITY

Karsten test - Nil (Impermeable)

### WEAR RESISTANCE

RWA1 EN 13892-5

### COMPRESSIVE STRENGTH

> 40 N/mm<sup>2</sup> PN-EN 13892-2

### FLEXURAL STRENGTH

15 N/mm<sup>2</sup> PN-EN 13892-2

### TENSILE STRENGTH

10 N/mm<sup>2</sup> BS 6319

### IMPACT RESISTANCE

IR20 EN ISO 6272-1

### BOND STRENGTH

> 1,5 MPa

SPEED OF CURE	+10°C	+20°C	+30°C
Light Traffic	36 hrs	24 hrs	16 hrs
Full traffic	72 hrs	48 hrs	48 hrs
Full chemical cure	12 days	7 days	7 days

## Standard colour chart



Grey 7710

Grey 7175

Beige 7184

Red 7720



Blue 7730

Blue 7178

Green 7740

Green 7190

The applied colours may differ from the examples shown.  
For a full colour chart and samples, contact your local CPG Europe office.

<sup>1</sup>The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site. <sup>2</sup>The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from CPG Eastern Europe), the degree of abrasion, maintenance and the nature of the dirt.

## Model Specification

<b>System:</b>	Peran ESD STB Compact
<b>Finish:</b>	Gloss
<b>Thickness:</b>	approx. 2,5–3 mm
<b>Colour:</b>	According to the catalog
<b>Producer:</b>	CPG Europe
<b>Supplier:</b>	Tremco CPG Poland Sp. z o.o.
<b>Telephone:</b>	+48 22 879 89 07

## Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via our website at [www.flowcrete.com.pl](http://www.flowcrete.com.pl).

## Products Included in this System

<b>Primer<sup>3</sup>:</b>	Peran STC (Protop 1000); Peran Copperstrip
<b>Primer with scatter:</b>	Peran ESD Primer (Peran ESD Primer WB); Peran ESD Compact Primer Sand
<b>Coating with scatter:</b>	Peran STC + Peran SL C; Peran ESD STB Sand
<b>Topcoat:</b>	Peran STC

<sup>3</sup> If other resins are used contact CPG Eastern Europe for further details.

Detailed application instructions are available upon request.


## Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

## Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

## System Design



## Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as „CPG Polska”) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer’s control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, CPG Polska cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.

25/05/21

CPG Eastern Europe  
ul. Marywilska 34, 03-228 Warsaw, Poland  
tel.: +48 22 879 8907  
email: [poland@cpg-europe.com](mailto:poland@cpg-europe.com)

 **Construction  
Products Group**  
Europe

[www.flowcrete.com.pl](http://www.flowcrete.com.pl)