



Isocrete SL Base

(3 - 50 mm)

A fast drying, self levelling screed for easy levelling of concrete floors before the installation of underlayments or thick floor coverings e.g. carpets, ceramic tiles or wood block.

Isocrete SL Base can be used as levelling layer underneath Isocrete 1500, SL Plus or bonded SL Renovation, or can be used on its own to level the concrete base to receive thick floor coverings.



Rapid Installation:

2,000m² per day for 7 mm thickness, under suitable conditions.



Flexible:

Hand or pump applied screed.



Protein Free:

It will not harbour bacteria.



Fast Drying & Setting:

Walk on after 2 - 4 hours and ready to cover after 1 - 3 days dependent on thickness/temperature/humidity.

Technical Profile*			
REACTION TO FIRE			
EN 13501-1	B _{ff} -s1	B _f - s1	
IMPACT RESISTANCE	BS 8204-1 Cat: A		
THERMAL RESISTANCE	50 °C Max		
COMPRESSIVE STRENGTH (28 DAYS)			
EN 13892-2	25 N/mm²	C25	
FLEXURAL STRENGTH (28 DAYS)			
EN 13892-2	6 N/mm²	F6	
ADHESION TO C30 CONCRI	ETE (28 DAYS)		
> 1N/mm ²			
SHRINKAGE	< 0.06%	< 0.06%	
MAXIMUM PARTICLE SIZE	2 mm		
PROTEIN CONTENT	Nil		
THICKNESS	3 - 50 mm Hand applied 7 - 50 mm Pump applied		
LAYING TEMPERATURE	5 – 25 °C		
FLOW RING (65 mm Diam. X 40 mm High)			
220 – 240 mm			
MIX RATIO PER 25KG	4.5 – 4.8 liti	res water	
SPEED OF CURE	10°C	20°C	
Walk on	4 - 8 hrs	2 - 4 hrs	
Full Traffic	3 days	3 days	
*These figures are typical properties ach 50 °C Relative Humidity. Isocrete SL Base	ieved in laboratory t	ests at 20 °C and at	
/ Prepared Base	ls	ocrete Primer	

Model Specification

Product	Isocrete SL Base
Thickness	3 – 50 mm

Preparatory work and application in accordance with manufacturer's instructions.

Products Included in This System

Primer	Isocrete Primer @ 0.05 kg/m²	
Or if dpm is required:		
DPM	Hydraseal DPM @ 0.5 kg/m²	
Sand scatter	Dry Silica Sand/Quartz grade 1 - 2 mm @ 2 kg/m²	
Floor Screed	Isocrete SL Base @ 11.9 kg/m² for 7 mm	

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH, tested in accordance with BS8204 and free from rising damp and ground water pressure. If above 75% RH, or no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Isocrete SL Base system, enabling the immediate installation of floor finishes once the screed has dried.

Installation Service

The installation can be carried out by any competent contractor. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.co.uk.

Drying Time

Moisture sensitive floor finishes can be installed when the screed is dry to 75% RH as per BS8203, typically after 1 - 3 days, dependent on thickness and ambient conditions (20 °C, 50% RH). After 24 hours curing (without draughts) ensure the area has sufficient ventilation to allow the screed to dry.

Protection on Completion

Ensure the screed is not subject to draughts and strong sunlight during the first 24 hours of curing as this may lead to cracking and crazing. Tape up doorways with polythene to prevent air movement. Prevent contamination by following trades e.g. plastering, including water spillage.

Focus on the Floorzone

Flowcrete is a market leader in specialist industrial and commercial flooring. Systems available include: underfloor heating, floor screeds, surface damp proof membranes, decorative floor finishes, seamless terrazzo, car park deck waterproofing, tank lining systems... to name just a few. Our objective is to satisfy your Floorzone needs.

Important Notes

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Terms and Conditions of Sale', copies of which can be obtained on request.

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [2018.11, 02 UK]